



SW8544

**Fasson 50u Wh. PET
TC/S1800/CCK130WH
IMP**

Top coated, white polyester film, characterized by high mechanical strength and good dimensional stability.

Applications



Salient Features

- Robust construction and packaging, suitable for ready to print sheet application.
- Low adhesive build-up on presses.
- Smooth print surface prolongs machine's life span.
- Quick ink drying time with good ink anchorage.
- Optimum adhesion on wide range of substrates.
- Good short term re-position ability.
- Consistent quality enabling high converting and printing efficiency.
- Defined Service guidelines.

Facestock

Top coated, white polyester, characterized by high mechanical strength and good dimensional stability.

Basis Weight:	62 gsm ± 10%	ISO 536
Caliper:	46 µm ± 10%	ISO 534

Adhesive

S1800 is a general purpose Emulsion based permanent adhesive.

Liner

A clay coated kraft liner featuring excellent strength characteristics.

Basis Weight:	130 gsm ± 10%	ISO 536
Caliper:	122 µm ± 10%	ISO 534

Laminate

Total Construction Caliper 180 µm ±10%

Performance data

Initial Tack	350	N/m	FTM 9 glass
Peel Adhes.180°	300	N/m	FTM 2 st. st.
Min. Appl. Temp.	5°C		
Service Temp.	-20°C to 80°C		

Applications and use

Typical applications include general purpose labels for Cosmetics, Toiletries and other health and beauty aid products, food and beverage products, promotional labeling, inventory and pharmaceutical & food industry labels: S1800 adhesive is in compliance with FDA 175.105 recommendations. Applications where paper labels are not acceptable due to environment conditions or any other factor.

Conversion/printing

The product is engineered to provide good lay flat characteristics desired for optimum performance in sheet applications. The product is suited to single and/or multicolor line printing by UV offset and digital printing.

Inks compatibility with sheet surface and press ink curing to be checked before run on the press. The product showcases excellent die cutting characteristics.


Exposure of sheets to high humidity conditions should be minimized. Since sheet surface is chemically top coated, Dyne testing is not indication of printability of the sheet.

Shelf life

Two years when stored at 22°C at 50% RH.

SW8544

Fasson 50u Wh. PET TC/S1800/CCK130WH IMP



50µ White PET TC

S1800

CCK130Wh IMP

Avery Dennison India Pvt. Ltd.

Gurgaon :

Narsinghpur Industrial Area,
Delhi – Jaipur Highway,
District Gurgaon, Haryana.
India. 122001

Tel: +91 124 4351200

Pune :

G-5, MIDC Ranjangaon Industrial Area,
Taluka - Shirur,
District – Pune, Maharashtra
India. 412220

Tel: +91 2138 664200

Bengaluru :

Plot No. 18 & 23, Peenya Industrial Area,
Phase-I, Yeshwantpur Hobli,
District – Bengaluru, Karnataka
India. 560058

Tel: +91 80 43316888

Warrenty

All statements, technical information and recommendations about AVERY DENNISON products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All AVERY DENNISON products are sold with the understanding that PURCHASER has independently determined the suitability of such products for its purposes. AVERY DENNISON products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Any product shown to the satisfaction of AVERY DENNISON within the time provided to be so defective shall be replaced without charge of AVERY DENNISON may issue credit in such amount as it seems reasonable however, in no event shall AVERY DENNISON be responsible for claims beyond the replacement value of the defective product or in any way

liable or responsible for consequential or incidental damages. NO EXPRESS WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE, EXCEPT AS SET FORTH ABOVE (WHICH IS MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES) SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERNATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON. No salesman, representative, or agent of AVERY DENNISON is authorized to give any guarantee, warranty or make any representation contrary to the above.