

Avery Dennison® 5300 Blockout Films

Features

- Total light block control, less than 0.001% light transmission
- Lustre finish face film, matching other Avery Dennison backlit sign products
- Dimensionally stable backing for easy converting
- Excellent conversion properties on computerised cutters
- Offers the choice of a white or a black face film
- Excellent adhesion to a wide variety of substrates
- Superior dimensional stability
- Excellent performance as second surface media
- Excellent performance for flat and slightly curved designs

Conversion

- | | |
|--|--|
| <input checked="" type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input checked="" type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Estat printing |
| <input checked="" type="checkbox"/> Die cutting | <input type="checkbox"/> Water based inkjet |
| <input type="checkbox"/> Thermal transfer | <input type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Screen printing | <input type="checkbox"/> UV Cured inkjet |

Uses

Avery Dennison 5300 Blockout Films are premium quality cast films that are especially designed for graphics involving internally illuminated light box applications.

Avery Dennison 5300 Blockout Films are designed to provide complete light blocking characteristics. Avery Dennison 5301 Blockout Film exhibits a uniformly lustre white finish and is uniformly black on the adhesive side. Avery Dennison 5303 Blockout Film has a black lustre finish and is uniformly white on the adhesive side. Avery Dennison 5300 Blockout Films are generally applied as a second surface substrate in combination with Avery Dennison 5500 QM Translucent films.

Description



Film: 100 micron premium cast vinyl



Adhesive: Permanent acrylic



Backing: One side coated bleached Kraft paper, 140gsm



Outdoor life: up to 5 years



Colours:
Avery Dennison 5301 White
Avery Dennison 5303 Black

Common Applications

- Internally illuminated signs
- Architectural signage

Physical characteristics

General

Calliper, face film	ISO 534	100 micron
Calliper, face film & adhesive	ISO 534	125 micron
Dimensional stability	DIN 30646	0.4 mm max.
Elongation	DIN 53455	100% min
Light Transmission		<0.001%
Adhesion, initial	FINAT FTM-1 Glass PMMA Polycarbonate ULTRALON IV	500 N/m 450 N/m 375 N/m 400 N/m
Adhesion, ultimate	FINAT FTM-1 Glass PMMA Polycarbonate ULTRALON IV	580 N/m 550 N/m 560 N/m 400 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22 °C/50-55 % RH	2 years
Accelerated aging	SAE J 1960 1500 hours exposure	No significant change
Durability **	Vertical exposure	5 years
Application temperature		Minimum: + 10°C
Service Temperature		-40 ° to +80 °C

Features

Application temperature		Minimum: + 10°C
Service Temperature		-40 ° to +80 °C

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70 °C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the normal middle European and central North American regions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased. Please refer to Avery Dennison Instructional Bulletin 1.3 for definitions and reductions based on the 'Zone System'.

***Information unavailable at time of printing.